

# XP BOND IN SELF-CURE MODE USED FOR LUTING PORCELAIN RESTORATIONS: 2-YEAR RECALL

MARCO FERRARI<sup>1</sup>, IVANOVIC CONIGLIO<sup>2</sup>, ELISA MAGNI<sup>2</sup>, MARIA CRYSAANTI CAGIDIACO<sup>3</sup>

## Abstract

**Purpose:** The aim of this clinical study was to evaluate, after 2 years of clinical service, certain clinical parameters of Empress II restorations luted under clinical conditions with XP BOND in combination with SCA and Calibra and cured in self-cure mode.

**Materials and methods:** Fifty-three restorations were placed in 38 patients from March 2006 until April 2006. No patient received more than two restorations. Luting procedures were performed following manufacturers' instructions. The restorations were evaluated for post-operative sensitivity, marginal discoloration, marginal integrity, secondary caries, maintenance of interproximal contact and fracture at baseline, after 2 weeks, 6 months, 1 year and 2 years of clinical service.

**Results:** At 2-year recall, post-operative sensitivity was reported in only 1 patient. Of the 53 restorations, only 2 showed bravo score and 2 charlie score for marginal integrity/stain. 1 restoration showed a bravo score at the vitality test. All other parameters showed alpha scores.

**Conclusions:** Almost all the evaluated restorations were in place and acceptable. The post-operative sensitivity recorded after using XP BOND with SCA and Calibra in self-cure mode was clinically acceptable.

**Keywords:** Ceramic crowns, Self-curing, Clinical Trial, Bonding

## Introduction

XP BOND was recently introduced and tested experimentally, showing high values in microtensile bond strength data compared to other systems when the adhesive was used with SCA and Calibra in self-cure mode.<sup>1</sup> Then, the baseline and 1- year reports of post-operative sensitivity and clinical parameters on XP Bond (DENTSPLY De Trey, Konstanz, Germany) used in combination with SCA and Calibra dual cure resin cement for luting indirect posterior porcelain restorations were published.<sup>2,3</sup> Post-operative sensitivity can be commonly found in vital teeth in which porcelain crowns were luted.<sup>4</sup>

When porcelain restorations are luted on vital abutments, a perfect bonding, which has to integrate all parts into one coherent structure, is necessary.<sup>5</sup> Luting material and

technique, as well as the substrate characteristics, therefore represent success determining factors.<sup>6</sup>

Among different combinations of adhesive-luting materials, dual-curing bonding systems are often the first choice<sup>7-16</sup> as they allow polymerization of the adhesive materials and the resin cement below thick ceramic restorations.

The aim of the present prospective clinical trial was to evaluate the 2-year clinical behaviour of Empress II restorations (Ivoclar-Vivadent, Schaan, Liechtenstein), luted with the adhesive system XP BOND (DENTSPLY DeTrey, Konstanz, Germany) with SCA (DENTSPLY Caulk, USA) and Calibra resin cement (DENTSPLY Caulk, USA), both used in self-cure mode.

## Materials and Methods

A consecutive sample of 53 restorations in 38 patients in need of one or two single-units was placed. Partial or full restoration was performed from the pool of patients accessing the department of Restorative Dentistry of the University of Siena. Patients' written consent to the trial was obtained after having provided a complete explanation of the aim of the study.

## Inclusion criteria

Males and females aged 18-60 years in good general and periodontal health were included.

<sup>1</sup> Professor and Chair

<sup>2</sup> Ph D Student

<sup>3</sup> Assistant Professor

Department of Dental Materials and Prosthodontics,  
University of Siena, Siena, Italy

### Corresponding author

Prof. Dr Marco Ferrari

Research Center for Dental Health,

19 Piazza Attias, 57120 Livorno, Italy

TEL: +39-586-892-283 FAX: +39-586-898-305

E-mail: md3972@mcclink.it

### Exclusion criteria

Patients with the following factors were excluded from the clinical trial:

1. Nonage (< 18 years);
2. Known pregnancy;
3. Disabilities;
4. Potential prosthodontic restoration of tooth;
5. Pulpitic, non-vital or endodontically treated teeth;
6. (Profound, chronic) periodontitis;
7. Deep carious defects (close to pulp, < 1mm distance) or pulp capping;
8. Heavy occlusal contacts or history of bruxism;
9. Systemic disease or severe medical complications;
10. Allergic history concerning methacrylates;
11. Rampant caries;
12. Xerostomia;
13. Lack of compliance;
14. Language barriers.

### Test stimuli and assessment

Before restoring the tooth, a pain measurement was performed utilizing a simple pain scale based on the response method. Response was determined by a one-second application of air from a dental unit syringe (at 40-65 p.s.i. at approximately 20°C), directed perpendicularly to the root surface at a distance of 2 cm and by tactile stimuli with a sharp #5 explorer. The patient was asked to rate the perception of the sensitivity experienced during this thermal/evaporative stimulation by placing a mark on a visual analog scale or line beginning at 0 and ending at 10 (where 0 = no pain and 10 = excruciating pain). In order to translate these scores into easily understood pain levels, a score of 0 was defined as no pain, 1-4 as mild sensitivity (which was provoked by the dentist air blast), and 5-10 as strong sensitivity (which was spontaneously reported by the patient during drinking and eating). Only patients scoring low on the analog scale were included in the study, whereas high score cases were excluded by the assumption that irreversible pulp inflammation may be sustaining the high sensitivity. The status of the gingival tissues adjacent to the test sites was observed at baseline and at each recall. Patients were recalled at our department for testing post-operative sensitivity after 2 weeks, 6 months, 1 year and 2 years.

### Clinical Procedure

For standardization purposes the same operator performed all the clinical procedures. Following anaesthesia, rubber dam was placed, all carious structures were excavated, and any restorative material was removed. Preparation was performed using conventional diamond burs in a high-speed hand piece, with no bevel on margins. The preparation design was dictated by the extent of decay and pre-existing restorations. The Residual Dentin Thickness (RDT) was evaluated on a periapical radiograph, and teeth with RDT thinner than 0.5 mm were excluded. After preparation, an impression of the prepared tooth was taken and sent to the laboratory. A temporary restoration was placed. One week later, the ceramic restorations were luted following manufacturer's instructions. The restorations were placed in the time period between March

and April 2006 and examined for post-operative sensitivity at baseline, after 2 weeks, 6 months, 1 year and 2 years by the same operator. At each recall, data regarding post-operative sensitivity, stability and longevity were collected with reference to the USPHS criteria. The following parameters were therefore assessed: Post-operative sensitivity: patient comfort with the restoration under function, cold and warm stimuli, and a gentle air stream was assessed. Sensitivity was defined by a scale from 0-10 as described above.

The null hypothesis tested was that XP Bond in self-cure mode cannot prevent post-operative sensitivity after 2 years of clinical service.

The other evaluated clinical parameters were: marginal discolouration and integrity, secondary caries, fracture, vitality test, retention and interproximal contacts.

### Results

The results are summarized in Tables 1-2. All 53 teeth were evaluated at baseline, after 2 weeks, 6 months, 1 year and 2 years. At baseline 3 patients showed pre-operative sensitivity in 5 teeth. 10 cases of post-operative sensitivity were observed at the 2-week recall and only 3 after 6 months. In one case, post-operative sensitivity increased from 0 to 6 immediately after luting the restoration (after the anesthetic effect wore off) but dropped to grade 3 after 6 months. In the 7 cases showing an increase in post-operative sensitivity after 2 weeks, hypersensitivity disappeared completely after 6 months. In 2 cases, a residual post-operative sensitivity of grade 2 still remained after 6 months. After 2 years of clinical service, minor post-operative sensitivity was present in only one patient. No adverse events/effects occurred. All other parameters showed alpha scores (Table 2).

After 2 years of clinical service almost all restorations were still clinically acceptable. Only two restorations failed.

### Discussion

According to the results of this clinical study, XP Bond in self-cure mode could prevent post-operative sensitivity after 2 years of clinical service.

With the intention of controlling any additional source of variation besides patient-related variability, one operator placed all the restorations in this clinical trial. 2 weeks after the placement of all restorations, post-operative sensitivity was found in around 19% (11 cases) of the restored teeth with a medium score of 1.9. Only one case of these 11 showed a high degree of post-operative sensitivity (score 6), whilst in other cases, the sensitivity was not spontaneous. The case in which the post-operative sensitivity was initially high (score 6) showed residual sensitivity after 1 year, but a clinically acceptable score 2. This observation is in agreement with a study that reported hypersensitivity to be the most common post-operative complication.<sup>16</sup> However, at the 6 month recall the score

**Table 1**

**Changes in pre- and post-operative sensitivity during the observation period of 2 years (1 = lowest sensitivity, 10 = highest sensitivity).**

Restoration	XP Bond / SCA / Calibra (n)		
	Pre-operative sensitivity and/or post-operative sensitivity 2 weeks after placement	Type of restoration	Post-operative sensitivity (2 year)
1 (#5)	6	Inlay (OD)	0
2 (#7)	1	Inlay (MOD)	0
3 (#10)	1	Inlay (MO)	0
4 (#11,14)	2	Onlay	0
5 (#26)	1	Onlay	0
6 (#20,29)	3	Inlay (OMD) and onlay	0
7 (#32)	1	Inlay(OM)	0
8 (#39)	4	Onlay	0
9 (#43)	3	Onlay	1
10 (#46)	1	Inlay (OMD)	0
11 (#53)	3	Inlay(OMD)	0

dropped from grade 6 (strong) to grade 3 (mild) and after 1 year to grade 2. At the 2-year recall almost no post-operative sensitivity was found.

After 1 year of clinical service, two restorations scored bravo for marginal stain/integrity, a score still clinically acceptable. This observation might be explained by the marginal wear of the composite luting cement undermining the mechanical support.<sup>8,13</sup> This observation was confirmed after 2 years of clinical service and lower scores were found for marginal stain/integrity. To prevent excessive marginal wear, it is therefore mandatory to have the narrowest gap possible between cavity preparation and ceramic restoration. Optimal fit (ranging from 50 to 100µm) is preferred,<sup>7</sup> particularly if the margins extend below the cementum-enamel junction.<sup>2,4</sup> Further clinical recalls will clarify whether the margins can be affected during longer clinical service.

The utilization of a correct bonding technique is mandatory to achieve good clinical results in ceramic inlays luting.<sup>2</sup> In direct resin restorations, the bonding agent is routinely light-cured prior to the insertion of the composite. In ceramic luting procedures, pre-curing of the adhesive resin may make restoration seating more difficult. The use of a self-cure bonding agent is also advantageous in this regard. In the present study a self-curing cement was chosen for luting the

restorations. Self-cure cements are also able to achieve an adequate degree of conversion at sites where light-curing may be hindered by the ceramic thickness. The setting time of the resin cement can be also directly correlated to room temperature, glass plate and mouth temperature.

It is important to understand the underlying chemical principles for each system. In the case of XP BOND, mixing with the self-cure activator SCA activates components of the SCA that are able to polymerize the adhesive interface on contact with the initiator from sufficiently initiated self- or dual-cure materials. Therefore, the self-cure mode for luting ceramic restorations of XP BOND mixed with SCA is only guaranteed when applied in combination with Calibra.

According to the data of this study, the mix of XP BOND with SCA in combination with self-activated Calibra showed clinically acceptable control of post-operative sensitivity at the 2 year recall. These findings will be re-evaluated during the next recall at 3 years.

### Conclusions

XP BOND with SCA and Calibra used in self-cure mode showed only in one case of 53 luted porcelain restorations a residual post-operative sensitivity of low intensity after 2 years of clinical service.

**Table 2a, 2b and 2c**

Performance criteria according to Ryge at 6 months (Table 2a), 1 year (Table 2b) and 2-year recall (Table 2c).

<b>Table 2a</b>					
<b>Criteria and number of restorations evaluated at 6 month recall</b>		<b>XP Bond / SCA / Calibra</b>			
		alpha	bravo	charlie	delta
Marginal discoloration and integrity	53	53	0	0	0
Secondary caries	53	53	0	0	0
Vitality test	53	53	0	0	0
Interproximal contacts	53	53	0	0	0
Retention	53	53	0	0	0
Fracture	53	53	0	0	0

<b>Table 2b</b>					
<b>Criteria and number of restorations evaluated at 1 year recall</b>		<b>XP Bond / SCA / Calibra</b>			
		alpha	bravo	charlie	delta
Marginal discoloration and integrity	53	51	2	0	0
Secondary caries	53	53	0	0	0
Vitality test	53	53	0	0	0
Interproximal contacts	53	53	0	0	0
Retention	53	53	0	0	0
Fracture	53	53	0	0	0

<b>Table 2c</b>					
<b>Criteria and number of restorations evaluated at 2 year recall</b>		<b>XP Bond / SCA / Calibra</b>			
		alpha	bravo	charlie	delta
Marginal discoloration and integrity	53	49	2	2	0
Secondary caries	53	53	0	0	0
Vitality test	53	52	1	0	0
Interproximal contacts	53	53	0	0	0
Retention	53	53	0	0	0
Fracture	53	53	0	0	0

### **Clinical relevance:**

The results of this 2-year study reveal good clinical performance of XP BOND in combination with SCA and Calibra in self-cure mode.

### **Acknowledgement**

This research was sponsored by DENTSPLY DeTrey, Konstanz, Germany.

### **References**

1. Raffaelli O, Cagidiaco MC, Goracci C, Ferrari M. XP BOND in self-cure mode used for luting porcelain restorations. Part A: microtensile test. *J Adhes Dent* 2007;9, Supplement 2: in press275-278..
2. Ferrari M, Goracci C, Grandini S, Cagidiaco MC. XP BOND in self-cure mode used for luting porcelain restorations. Part B: placement and 6-month report.post-operative report... *J Adhes Dent* 2007;9, Supplement 2: in press279-282.
3. Ferrari M, Coniglio I, Magni E, Cagidiaco MC. XP Bond in self-curing mode used for luting porcelain restorations: 1 year recall. *Int Dent S Afr* 2007;9(4):44-51
4. Frankenberger R, Krämer N, Petschelt A. Technique sensitivity of dentin bonding: effect of application mistakes on bond strength and marginal adaptation. *Oper Dent* 2000;25:324-330.
5. Ferrari M, Mason PN. Adaptability and microleakage of indirect resin inlays: an in vivo investigation. *Quintessence Int* 1993;24:861-865.
6. Ferrari M, Mason PN, Fabianelli A, Cagidiaco MC, Kugel G, Davidson CL. Influence of tissue characteristics at margins on leakage of class II indirect porcelain restorations. *Am J Dent* 1999;12:134-142.
7. Dagostin A, Ferrari M. In vivo bonding mechanism of an experimental dual cure enamel-dentin bonding system. *Am J Dent* 2001;14:105-108.
8. Fabianelli A, Goracci C, Bertelli E, Davidson CL, Ferrari M. A clinical trial of Empress II Porcelain inlays luted to vital teeth with a dual-curing adhesive system and a self-curing resin cement. *J Adhes Dent* 2006; 8(6):427-431.
9. Ferrari M, Dagostin A, Fabianelli A. Marginal integrity of ceramic inlays luted with a self curing resin system. *Dent Mater* 2003;19:270-276.
10. Krämer N, Frankenberger R, Pelka M, Petschelt A. IPS Empress inlays and onlays after four years- a clinical study. *J Dent* 1999;28:325-331.
11. Krämer N, Frankenberger R. Clinical performance of bonded leucite –reinforced glass ceramic inlays and onlays after eight years. *Dent Mat* 2005;21:262-271.
12. Lee IB, Um CM. Thermal analysis on the cure speed of dual cured resin cements under porcelain inlays. *J Oral Rehabil* 2001;28:186-197.
13. Manhart J, Scheibenbogen-Fuchsbrunner A, Chen HY, Hickel R. A 2-year clinical study of composite and ceramic inlays. *Clin Oral Invest* 2000;4:192-198.
14. Milleding P, Örtengren U, Karlsson S. Ceramic inlay systems: some clinical aspect. *J Oral Rehabil* 1995;22:571-580.
15. Molin MK, Karlsson SL. A randomized 5-year clinical evaluation of 3 ceramic inlay systems. *Int J Prosthodont* 2000;13:194-200.
16. Krämer N, Lohbauer U, Frankenberger R. Adhesive luting of indirect restorations. *Am J Dent* 2000;13:60-76.